



TECHNICAL DATA SHEET

PRODUCT: POLYVINE Acrylic Enamel

PRODUCT DESCRIPTION

An ultra hard, high quality, acrylic, sandable coating with a gloss finish. This coating dries to a coloured film with extremely good sanding properties allowing a very high quality of finish to be obtained. Acrylic Enamel is specially formulated to bond to a wide range of surfaces. Wood, metal, laminate and glass.

SURFACE PREPARATION

Ensure the surface to be coated is clean and free from grease, wax or polish

APPLICATION

Apply 2-3 coats.
Dilute 10% with water to prime porous surfaces.
By good quality synthetic brush, recommended, or by airbrush.
Low-pressure spray.
Rollers are not recommended, stippling may occur. Stir well.
If cissing occurs, rub onto affected area with a damp cloth to break the surface tension and re-apply.

CAUTION

Test finish for adhesion.
Do not apply over uncured oils.

COVERAGE

Approx. 10-20 sq. m per litre. 108-215 sq. ft per US qt.

CLEAN UP

Any equipment used can be cleaned using soap and water before the coating dries. Wipe any excess off surfaces with a damp cloth. Any dried deposits will need a paint stripper to remove them.

HEALTH AND SAFETY

In case of: skin contact –wash off with soap and water before the clear coat dries. For people with delicate skin it is advisable to wear gloves.

Eye contact – rinse with clean water for 15 minutes, seek medical attention if irritation persists.

Inhalation - Acrylic Enamel does not give off harmful vapours, however it is better to work in well ventilated areas. If there is irritation or an allergic reaction remove the victim to fresh air, and if irritation persists seek medical attention.

Ingestion - Give victim a drink of water and seek medical attention.

FILM PROPERTIES

DRY FILM: Gloss.

DRYING TIME: 1 to 2 Hours @ 20°C / 70°F

Low temperature/high humidity increases drying time.

CURE TIME: Up to 5 days @ 20°C / 70°F

RECOAT TIME: Up to 2 Hours @ 20°C / 70°F

HARDNESS: Highly Durable

NON YELLOWING

NO FIRE HAZARD Before or during use, or in the cured state.

RESISTANT TO: Water and abrasion.

PACKAGING

20ml, 50ml, 100ml.

STORAGE

Store in unopened containers in a cool dry place away from direct sunlight.

The information supplied herein is accurate to the best of our knowledge. Since conditions and methods are beyond our control, no warranty is expressed or implied. You are advised to access the suitability of the product on a test area before application

Further information may be obtained from:

POLYVINE LIMITED

Severn Distribution Park

Sharpness, Berkeley,

Gloucestershire.

GL13 9UQ

United Kingdom

Telephone No. 0870 787 3710

International +44 870 787 3710

Fax: 0870 787 3709

Email info@polyvine.co.uk

Date of issue: October 2008